




20M, 31M (METRIC)	Cut Type	Speed m/min	Feed (mm/rev)				
			1.6	3	6	10	12
● CFRP, AFRP (Carbon Fiber, Aramid Fiber)	Slot	120	0.030	0.060	0.120	0.230	0.305
	Profile	150	0.030	0.060	0.120	0.230	0.305
	Light	250	0.070	0.140	0.280	0.525	0.700
● GFRP (Fiberglass)	Slot	100	0.030	0.060	0.120	0.230	0.305
	Profile	120	0.030	0.060	0.120	0.230	0.305
	Light	200	0.070	0.140	0.280	0.525	0.700
● CARBON, GRAPHITE	Slot	145	0.040	0.075	0.150	0.290	0.380
	Profile	185	0.040	0.075	0.150	0.290	0.380
	Light	300	0.090	0.175	0.350	0.655	0.875
● PLASTIC	Slot	245	0.040	0.075	0.150	0.290	0.380
	Profile	305	0.040	0.075	0.150	0.290	0.380
	Light	505	0.090	0.175	0.350	0.655	0.875
MACHINABLE CERAMIC, MACHINABLE GLASS	Slot	10	0.015	0.030	0.060	0.115	0.150
	Profile	15	0.015	0.030	0.060	0.115	0.150
	Light	25	0.035	0.070	0.135	0.260	0.350

Cut Type		
Slot	Profile	Light
31M Rw = D <sub>1</sub> Ad = D <sub>1</sub>	31M Rw = .5 x D <sub>1</sub> Ad = 1.5 x D <sub>1</sub>	20M, 31M Rw = .05 x D <sub>1</sub> Ad = L <sub>2</sub>
		

$rpm = (1000 \times m/min) / (3.14 \times D_1)$   
 $mm/min = (mm/rev) \times rpm$

- maximum recommended depths shown
- adjust speed and feed based upon resin type and/or fiber structure
- reduce speed when overheating causes melting or damage to resin
- reduce feed if delamination or fraying occurs
- finish cuts typically require reduced feed and cutting depths
- rates shown are for use without coolant; rates may be increased with coolant use
- dust collection is vital when machining dry
- diamond coating will increase tool life in graphite and composite materials
- refer to the SGS Tool Wizard for more complete technical information (available at )